

## Calculations of Permanent Magnet Using Distributed-Parameters Equivalent Circuit

Emad Said Addasi

Department of Electrical Engineering, Engineering Faculty, Tafila Technical University.

**Abstract:** In the current work a procedure for determination the ratio of the length to the diameter of the permanent magnet, at which the ratio of the leakage flux to the desired flux through the magnet body is minimized, has been developed. The permanent magnet has been modeled by an electric equivalent circuit with distributed parameters, which describe the real physical phenomena in the permanent magnet. A cylindrical permanent magnet has been studied and calculated. In the equivalent circuit, of this cylindrical permanent magnet, is taken into account the difference of magnetic potentials between the magnetic poles. So for cylindrical permanent magnet in order to get less, relatively, leakage flux the permanent magnet must be designed with the ratio of its length to the radius of 1.97 times. The developed procedure enables us to determine the permanent magnet dimensions with higher, relatively, magnetic flux, which makes the magnet more efficient. So this will be very useful in permanent magnet design.

**Key words:** Leakage flux, hysteresis loop, distributed parameters, cylindrical form

### INTRODUCTION

Permanent magnets have many different applications, such as in electrical measuring instruments, magnetic bearing (Andrew J., *et al.*, 2003; Jiles, D.C.; S.H. Song, 2007; Hawkins, L.A., 1997 and Lee S.J., *et al.*, 2007) and electrical machines (M.A. Rahman, *et al.*, 2006; S. Vaes-Zadeh; A. Hassanpour, 2007; Lukaniszyn M., *et al.*, 2003; Mendrela E.A., *et al.*, 2003; Lukaniszyn M., *et al.*, 2002; Jagiela M.; Wrobel R., 2003; Wrobel R. and Mellor P., 2003) as a source of the magnetic field and in many other applications (Wrobel R. nd Mendrela E.A., 1999; Kenny A., *et al.*, 2001; Lukaniszyn M. and Jagiela M., 2003).

Magnetic field is necessary in operation of many different machines and devices. To get magnetic field may be used electromagnetic circuits or permanent magnets made from hard-iron ferromagnetic materials with high coercive magnetomotive force. Permanent magnets are made from different alloys, such as iron, aluminum, nickel, copper, cobalt, titanium and other materials (Belov K.P., 1987; Osin I.L. and Shakaryan U.G., 1990). Many works focus on the behavior and properties of permanent magnets (Andrew J., *et al.*, 2003; Melikhov Y. and Jiles D.C., 2007; Lee S.J., *et al.*, 2007; Altman A.B. and Vernikovskiy E.E., 1980; Zimin E.F. and Kochanov E.S., 1985). But the problem here is how to design the permanent magnet and how to make calculations in order to determine its construction with optimal dimensions, mass, cost and other parameters. Therefore, the main objective of the research is to find the ratio of the length to the diameter of the permanent magnet, at which the ratio of the leakage flux to the desired flux through the magnet body is minimized.

#### **Permanent Magnet Calculations:**

The main purpose of this paper is to develop a procedure for calculations of the permanent magnet dimensions in order to get minimum leakage flux relative to the useful desired magnetic flux. These calculations are based on the magnetization curve of the used material as shown in figure 1.

Let the permanent magnet has a cylindrical form as shown in figure 2. In real permanent magnet its surface does not have the same magnetomotive force. Therefore, it has different magnetic potentials at different points of its height. For simplification calculations, suppose that the magnetic potential is linear distributed along the magnet.

The total magnetic flux of this magnet is the sum of leakage flux from the side surface and the flux through the magnet itself as shown in figure 2, and may be determined by the following equation:

$$\Phi = \Phi_{mag} + \Phi_l,$$

**Corresponding Author:** Emad Said Addasi, Yanbu Industrial College, KSA, Electrical & Electronics Engineering Technology Department, P.O. Box 40, Al-Eys 66141, Tafila, Jordan.  
Tel.: +966.556046076 E-mail: emad\_addasi@yahoo.com

where

- $\Phi$  - the total magnetic flux of the permanent magnet,
- $\Phi_{\text{mag}}$  - the magnetic flux through the magnet itself,
- $\Phi_l$  - the leakage magnetic flux from the side surface.

But magnetic flux through the permanent magnet side will vary along it, thus it is better to determine the total magnetic flux with respect to the cross sectional area of the permanent magnet poles. Therefore, the shown in figure 3 equivalent circuit of the permanent magnet may be used, where:

- $R_i$  - the magnetic reluctance of the  $i^{\text{th}}$  element disc with the height  $dl$  of the permanent magnet as shown in figure 2, ( $i = 1, 2, 3, \dots, n$ ),
- $\rho_i$  - the magnetic permeance through the air per unit of length at the permanent magnet surface between two adjacent elemental discs of the permanent magnet, ( $i = 1, 2, 3, \dots, n-1$ ).

The equivalent circuit of figure 3 may be replaced by the simplified equivalent circuit of figure 4, where  $F = H \cdot l$ ,

- $F$  - the magnetomotive force,
- $l$  - the equivalent length of the permanent magnet,
- $H$  - the mean value of demagnetizing magnetic field intensity inside the permanent magnet,
- $R_{eq}$  - the equivalent magnetic reluctance of the whole permanent magnet calculated from the equivalent circuit in figure 3.

Demagnetizing magnetic field intensity may be determined using the magnetization curve of the permanent magnet material (the hysteresis loop).

The value of  $R_{eq}$  may be calculated as follows (Neyman L.R. and Kalantarov P.L., 1959):

$$R_{eq} = R_o \cdot \tan(\gamma \cdot l),$$

where  $R_o = \sqrt{R/\rho}, \gamma = \sqrt{R \cdot \rho}$

Thus  $R_{eq} = \sqrt{R_i/\rho_i} \cdot \tan(l \cdot \sqrt{R_i/\rho_i})$

And from magnetization curve, residual magnetic flux density may be determined. Thus the magnetomotive force can be found, in first approximation, as follows:

$$F = H_1 \cdot l = \Phi \cdot R_{eq} = \frac{B_r \cdot \pi \cdot d^2}{4} \sqrt{R_i/\rho_i} \cdot \tan(l \cdot \sqrt{R_i/\rho_i}),$$

where:

- $H_1$  - the first approximation of the mean value of the demagnetizing magnetic field intensity in the permanent magnet body,
- $B_r$  - the residual magnetic flux density,
- $\frac{\pi \cdot d^2}{4}$  - the cross sectional area of the permanent magnet.

From the last equation yields:

$$H_1 = \frac{B_r \cdot \pi \cdot d^2}{l \cdot 4} \sqrt{R/\rho} \cdot \tan(\varphi) \cdot \sqrt{R/\rho}.$$

It is well known that  $B_r$  is the residual magnetic flux density when the external magnetizing force is removed. Therefore, from the magnetization curve, it is clear that the residual flux density will be reduced to the value  $B_{r2}$  as shown in figure 1. As a result of that the magnetic flux decreases:

$$\Phi = B_{r2} \cdot \pi \cdot r^2,$$

where  $r = d/2$ .

And so the resultant demagnetizing magnetic field intensity decreases also:

$$H_2 = \frac{B_{r2}}{l} \pi \cdot r^2 \cdot \sqrt{R/\rho} \cdot \tan(\varphi) \cdot \sqrt{R/\rho}.$$

Thus the new value of the mean demagnetizing magnetic field intensity  $H_2$  will be less than the value of  $H_1$ . In the other hand, this decrease of  $H$  makes the residual flux density to increase to be  $B_{r1}$  as shown in figure 1. The last one gives a new smaller  $H$  and so on.

The values of the demagnetizing magnetic field intensity  $H_1$  and  $H_2$  are the limit values of the studied case:  $H_1$  is the upper limit and  $H_2$  is the lowest limit. Thus the geometric mean value of  $H$  may be found:  $H = \sqrt{H_1 \cdot H_2}$ .

Using the magnetization curve, the last equation may be rewritten as follows:

$$H = \frac{\sqrt{B_{r2} \cdot B_r}}{l} \pi \cdot r^2 \cdot \sqrt{R_i/\rho_i} \cdot \tan(\varphi) \cdot \sqrt{R_i/\rho_i} \tag{1}$$

To be able to calculate  $H$  the values of  $R_i$  and  $\rho_i$  must be known. First one may be found by the following equation:

$$R_i = \frac{dl}{\mu \cdot A} = \frac{dl}{\mu \cdot \pi \cdot r^2} \tag{2}$$

where

$\mu = B/H$  - the magnetic permeability of the permanent magnet material.

The value of the magnetic permeability depends on the point on magnetization curve at which it operates. And so if this point is not known it is impossible to find the value of  $\mu$ . And if  $\mu$  is not known then  $R_i$  cannot be determined and so the operating point cannot be found.

To avoid this paradox or dead point, instead of the permeability value may be used the ratio  $B/H$  at the point of maximum energy  $(BH)_{max}$  (Osin I.L. and Shakaryan U.G., 1990).

Thus magnetic reluctance may be calculated using equation (2) assuming that  $\mu = B/H$  at the point of maximum energy  $(BH)_{max}$  of the magnetization curve of permanent magnet material.

For magnetic permeance determination, the condition of linear magnetic potential along the permanent magnet surface may be used (Altman A.B. and Vernikovskiy E.E., 1980). And by using the spheroid equivalent of the cylindrical permanent magnet (Mizyuk L.Ya., 1984) permeance may be found:

$$\rho_i = \frac{\pi \cdot \mu_o \cdot l \left(1 - \frac{r^2}{l^2} \ln \frac{2l}{r}\right)}{3 \left[ \ln\left(\frac{2l}{r}\right) - 1 \right]} \quad (3)$$

Substituting equation (2) and (3) in (1) yields:

$$H = \frac{\sqrt{B_{r2} \cdot B_r}}{l} \pi r^2 \sqrt{\frac{3 \left[ \ln \frac{2l}{r} - 1 \right]}{\mu \pi^2 r^2 \mu_o \left[ 1 - \frac{r^2}{l^2} \ln \frac{2l}{r} \right]}} \tan \left[ \frac{\mu_o \left[ 1 - \frac{r^2}{l^2} \ln \frac{2l}{r} \right]}{3 \mu r^2 \left[ \ln \frac{2l}{r} - 1 \right]} \right]$$

At  $r \ll l$  the last equation may be simplified:

$$H = \frac{\sqrt{B_{r2} \cdot B_r}}{l} A \sqrt{\frac{3 \left[ \ln \frac{2l}{r} - 1 \right]}{A \cdot \pi \cdot \mu \cdot \mu_o}} \tan \left[ \frac{\mu_o \cdot \pi}{3 \mu A \left[ \ln \frac{2l}{r} - 1 \right]} \right]$$

where

$A = r^2$  - the cross sectional area of the permanent magnet.

The distributed parameters  $R_i$  and  $R_{if}$  give ability for determination of the optimal ratio of the permanent magnet length ( $l$ ) and radius ( $r$ ). Assuming that  $\mu \gg \mu_o$  the total permeance of the permanent magnet body and the permeance for leakage flux may be calculated as follows:

$$\rho_o = \frac{1}{R \cdot l} = \frac{\mu \cdot A}{l} \quad (6)$$

$$\rho_{if} = \rho_i \cdot l = \frac{\pi \cdot \mu_o \cdot l \left(1 - \frac{r^2}{l^2} \ln \frac{2l}{r}\right)}{3 \left( \ln \left(\frac{2l}{r}\right) - 1 \right)} \quad (7)$$

where:

- $\rho_o$  - the total permeance of the permanent magnet body,
- $\rho_{if}$  - the total permeance for leakage flux.

By dividing equation (7) by equation (6) yields:

$$\frac{\rho_{\text{fl}}}{\rho_{\text{b}}} = \frac{\mu_0 \left[ \frac{l^2}{r^2} - \ln \left( 2 \frac{l}{r} \right) \right]}{3 \cdot \mu \cdot \left[ \ln \left( 2 \frac{l}{r} \right) - 1 \right]} \quad (8)$$

Assuming that  $X = \frac{l}{r}$  - the ratio of the permanent magnet length to its radius, the last equation becomes:

$$\frac{\rho_{\text{fl}}}{\rho_{\text{b}}} = \frac{\mu_0 \left[ X^2 - \ln 2 X \right]}{3 \cdot \mu \cdot \left[ \ln (2 X) - 1 \right]} \quad (9)$$

To get minimum ratio of the total permeance of the leakage flux to the total permeance of the permanent magnet body, it is useful to find the derivation of this ratio and equal it to zero.

$$\frac{d}{dX} \left( \frac{\rho_{\text{fl}}}{\rho_{\text{b}}} \right) = 0 .$$

And finally the last equation gives:

$$2 \cdot \ln (2 X) - 3 + \frac{1}{X^2} = 0$$

This equation has two solutions:  $X \approx 1.97$      $X \approx 0.626$  . Considering the assumed condition  $r \ll l$ , the first solution only is acceptable. Therefore, the ratio of the permanent magnet length to its radius, which gives minimum ratio of leakage flux to the flux through the body of the permanent magnet itself, is equal to 1.97 ( $l/r=1.97$ ). And at this value of ( $l/r$ ) the ratio of the total permeance for leakage flux to the total permeance of the permanent magnet body will be:

$$\frac{\rho_{\text{fl}}}{\rho_{\text{b}}} = 2.254 \frac{\mu_0}{\mu} .$$

Therefore, the developed procedure for determination the permanent magnet dimensions, finally, gives simple equations for calculations and avoids the complexity in other works. But for short-length permanent magnet the ratio of the magnetic permeance through side surface to the magnetic permeance through magnet pole faces using the last approximated equation will be:

$$\frac{\rho_{\text{fl}}}{\rho_{\text{m}}} = \frac{\pi^2 \cdot \mu_0 \cdot r}{8 \cdot \mu_0 \cdot r} \approx \text{constant} .$$

This study was conducted in Tafila Technical University in Jordan and in Yanbu Industrial College in KSA in 2006-2007.

## RESULTS AND DISCUSSION

### Results:

In this research has been developed a procedure for determination the ratio of the length to the diameter of the permanent magnet, at which the ratio of the leakage flux to the desired flux through the magnet body




Fig. 1: Magnetization and demagnetization curves of the permanent magnet material.




Fig. 2: The cylindrical permanent magnet.




Fig. 3: The equivalent circuit of the permanent magnet with distributed parameters.

is minimized. For cylindrical permanent magnet to get less, relatively, leakage flux the ratio ( $l / r$ ) must be equal to 1.97. Then ratio of the total permeance for leakage flux to the total permeance of the permanent magnet inside will be  $2.254 \mu_0 / \mu$ . Therefore, these result are restricted to the cylindrical permanent magnet with  $l \gg r$ . But for short-length permanent magnet, unlike for long permanent magnet, the value of

permeance through the useful (desired) magnetic flux path and through the leakage magnetic flux path do not depend on the length of the permanent magnet. But they depend only on the magnet diameter.



**Fig. 4:** The equivalent circuit of the permanent magnet model.

**Discussion:**

The permanent magnet has been modeled by an electric equivalent circuit with distributed parameters, which describes the real physical phenomena in the permanent magnet. A procedure for permanent magnet calculations has been developed. Such a procedure enables one to determine the permanent magnet dimensions, particularly the ratio between the length and the diameter, at which the ratio of the leakage magnetic flux to the desired flux through the magnet body is minimized. This will be very useful in permanent magnet design.

For a permanent magnet with cylindrical form the ratio of the permanent magnet length to its radius, which gives minimum ratio of leakage magnetic flux to the flux through the body of the permanent magnet itself is equal to 1.97 ( $l / r = 1.97$ ). These results may be useful in permanent magnet design.

But in this research the final results are restricted to the cylindrical form permanent magnet. So for permanent magnets with other shapes additional study is required. The significance of these results, if compared with other works, is in using the distributed parameters equivalent circuit for getting the optimal ratio ( $l / r$ ) for the permanent magnet.

**ACKNOWLEDGMENT**

The author Addasi Emad Said thanks the administration of his affiliation: Tafila Technical University for its support in preparing this article.

**REFERENCES**

Andrew, J. Provenza, Andrew Kenny and Alan B. Palazzolo, 2003. An Integrated Magnetic Circuit Model and Finite Element Model Approach to Magnetic Bearing Design. NASA / TM-2003-212297, IECEC, USA.

Jiles, D.C. and S.H. Song, 2007. Magnetic structures in Pr6Ni2Si3 and Pr5Ni2Si3, Journal of Applied Physics, 101.

Hawkins, L.A., 1997. Shock Analysis for a Homopolar, Permanent Magnet Bias Magnetic Bearing System. International Gas Turbine and Aeroengine Congress and Exhibition, Orlando, 97-GT-230.

Melikhov, Y. and D.C. Jiles, 2007. Modelling of non-linear behavior and hysteresis in magnetic materials (Invited), Handbook of Magnetism and Advanced Magnetic Materials, Editors H.Kronmuller and S.S.Parkin, John Wiley & Sons Scientific Publishers

Lee, S.J., J.E. Snyder, Y. Melikhov, D.C. Jiles and N. Ranvah, 2007. Magnetic and Magnetoelastic Properties of Substituted Cobalt Ferrites, American Physical Society March Meeting, Denver CO, U.S.A., March 5-9.

Rahman, M.A., M. Nasir Uddin and M.A. Abido, 2006. "An Artificial Neural Network for Online tuning of a Genetic Based PI Controller for Interior Permanent Magnet Synchronous Motor Drive", Canadian Journal of Electrical & Computer Engineering, 31.3: 159-165.

Vaes-Zadeh, S. and A. Hassanpour Isfahani, 2007. Enhanced Modeling of Linear Permanent Magnet Synchronous Motors, IEEE Trans. On Magnetics, 43(1): 33-39.

Lukaniszyn, M., M. Jagiela and R. Wrobel, 2003. Electromechanical Properties of a Disc-Type Salient-Pole Brushless DC Motor with Different Pole Number. International Journal for Computations in Mathematics and electrical and electronic Engineering COMPEL, Emerald Press, 22(2): 285-303.

Mendrela, E.A., R. Beniak and R. Wrobel, 2003. Influence of Stator Structure on Electromechanical Parameters of Torus-Type Brushless DC Motor. IEEE Transactions on Energy Conversion, 18(2).

Lukaniszyn, M., E.A. Mendrela and M. Jagiela, 2002. 3-D Calculations of Magnetic Field and Torque in a Brushless DC Motor with Co-Axial Flux in the Stator. *Electromagnetic field in Electrical Engineering, Studied in Applied Electromagnetics and Mechanics*, IOS Press, Amsterdam, Netherlands, 22: 248-253.

Jagiela, M. and R. Wrobel, 2003. An Influence of permanent Magnet Shape on the Torque Ripple of the Disc-Type DC Motor. *International Symposium in Electromagnetic Fields ISEF'2003* 18-20 September, Maribor, Slovenia.

Wrobel, R. and P. Mellor, 2003. The Design of Permanent Magnet Machine Rotors Using a Genetic Algorithm. *The Fifth Joint UK Magnetics Workshop, JMW'2003* 2-4 July, Glasgow, UK, pp: 89.

Wrobel, R. and E.A. Mendrela, 1999. Influence of the Stator Core Design of Torus Brushless DC Motor on Magnetic Field and Torque Calculated in 3-D Space. *International Conference on the Computation of Electromagnetic Field COMPUMAG'1999*, October 25-28, Sapporo, Japan, pp: 94-95.

Kenny, A., A. Provensza, A. Palazzolo, R. Beach, A. Kascak, S. Lei, Y. Kim, U. Na and G. Montague, 2001. Novel Actuator for Magnetic Suspensions of Flywheel Batteries. *ASME Thirty-Sixth International Energy Conversion Engineering Conference, IECEC'2001-AT-84*.

Lukaniszyn, M. and M. Jagiela, 2003. Optimization of Permanent Magnet Shape for Minimum Cogging Torque Using a Genetic Algorithm. *14th International Conference Electromagnetic Fields COMPUMG'2003*, Saratoga Springs, USA.

Belov, K.P., 1987. *Magnetic-Streak Phenomena and There Applications*. Nauka, Moscow.

Osin, I.L. and U.G. Shakaryan, 1990. *Electrical Machines, Synchronous Machines*, Vishaya Shkola, Moscow.

Altman, A.B. and E.E. Vernikovsky, 1980. *Permanent Magnet, Handbook*, Energy, Moscow.

Zimin, E.F. and E.S. Kochanov, 1985. *Measurement of Parameters of Electrical and Magnetic Fields in Conductive Medium*. Energy-Atom-Ezdat, Moscow.

Neyman, L.R. and P.L. Kalantarov, 1959. *Principles of Electrical Engineering. Part Tow*, Gos-Energy-Ezdat, Moscow.

Mizyuk, L.Ya., 1984. *Converters for Measuring Magnetic Field Intensity of Low-Frequency Magnetic Fields*. Naukova-Dumka, Kiev, Ukraine.